

DI OCTYLSULPHIDE AS A CORROSION INHIBITOR FOR ZINC METAL IN ACIDIC SOLUTION

S.S Syed Abuthahir^{1*} & M.Raja¹

¹PG and Research Department of Chemistry, Jamal Mohamed College (Autonomous), Tiruchirappalli, Tamilnadu, India.

Received: July 20, 2018

Accepted: August 30, 2018

ABSTRACT

The inhibitive action of Di octylsulphide on zinc metal has been evaluated in 0.5N HCl as corrosion medium using weight loss, gasometric and thermometric techniques. Corrosion parameters such as inhibition efficiency and corrosion rates were calculated to assess the performance of the inhibitor. The result shows that the inhibitor has good corrosion inhibition efficiency. The inhibition efficiency increase with increase in the inhibitor concentration because of formation of protective film over the zinc metal surface. The protective film which blocks the active sites of zinc metal and retards the zinc metal from its dissolution. It follows that chemisorptions mechanism. The Temkin adsorption isotherm gave the best appropriate for the inhibitor. The surface morphology of the zinc metal was characterized by Scanning electron microscopy (SEM) and atomic force microscopy (AFM) in the absence and presence of the inhibitor.

Keywords: Acidic solutions, Atomic force microscopy, Di octylsulphide, Gasometry, Scanning electron microscopy, Thermometry, Weight loss, Zinc corrosion.

1. INTRODUCTION

Corrosion of metals and alloys consequence in the loss of many important characteristics such as malleability, flexible and conductance. The proposed action to be earning to control the corrosion process is to isolate the metals and alloys from the corrosive environments. Use of corrosion inhibitors is one of the available methods for metals against corrosion. Organic compounds with heteroatom, multiple bonds and aromatic rings proved to be effective corrosion inhibitors. Diversity of organic compounds were used as corrosion inhibitors for zinc metal in different environments [1-9]. These inhibitors restraint the corrosion action by adsorption on to the metal surface. In this work, The Di octylsulphide used as a corrosion inhibitor for zinc metal in 0.5 N HCl acid solution by weight loss, gasometry and thermometric methods. The inhibition efficiency and corrosion rates were calculated from weight loss, gasometric and thermometric methods. The surface film formed over the zinc metal has been characterized by SEM and AFM. An organic compound to interact with a metal surface is closely connected with chemical adsorption. The efficiency of this inhibitor is correlated to the presence of polar functional groups with S, O or N atoms, δ -electrons in the molecule.

2. EXPERIMENTAL SECTION

2.1 Materials and Methods

Specimen preparation

Composition of zinc specimen: lead 0.03%, cadmium 0.04%, iron 0.001% and the quantity left over being zinc and size of $4 \times 2 \times 0.08$ cm were used for weight loss, gasometry and thermometry studies. Zinc metal specimens were polished with a sequence of emery papers of different grades from 400-1200, degreased with absolute ethanol and dried. The inhibitor compound, Di octylsulphide was customary Alfa Aesar Chemicals United Kingdom. The working surface was at a subsequent time ground with acetone followed by double-distilled water, dried in warm air and then stored in moisture-free desiccators before ducking in a corrosive medium. [10].

2.2 Preparation of Organic inhibitor

Di octylsulphide was prepared by different concentration with 100 ml of ethanol. Test solutions with different concentrations from 0.19 g/L to 1.32 g/L were prepared by diluting the stock solution in 0.5 N HCl [11,12].

2.3 Weight loss measurements

Zinc specimens with dimensions of 3.0 cm \times 3.0 cm were polished, degreased with acetone and dried. A Mettler balance – M5 type was used to weigh the zinc specimens to an accuracy of 0.0001 gm. The specimens were deep in a beaker containing 100 ml of 0.5 N HCl without and with 5,10,30,50,100 mM concentrations of the inhibitor (organic inhibitor) using glass hooks and rods. The effect of the

temperature was also studied an contact period of 2 hours using a water-circulating thermostat (Equitron). All the test standard systems were open to the air. After 2 hours, the specimens were taken out, washed with distilled water and re-weighed [13,14]. To obtain good reproducibility, experiments were carried out in triplicate, and the average values were be given. The weight loss was recorded, and the inhibition efficiency as well as the surface area coverage was calculated using the following equation [15,16].

$$\text{I.E (\%)} = [W_0 - W_i / W_0] 100$$

$$\theta = W_0 - W_i / W_0$$

Where W_0 and W_i are the weight loss of the metal in the absence and presence of the inhibitor separately. The corrosion rate (C.R) of the metal was calculated by using the following equation.

$$\text{C.R (mmy)} = \frac{87.6 / W}{A t D}$$

Where W is the weight loss of the zinc metal (mg), A is the surface area of the metal specimen (cm^2), t is the frostbite time (h) and D is the density of the metal (g/cm^3).

2.4 Gasometric measurements

The acidic corrosion of zinc is characterised by evolution of hydrogen and the rate of corrosion is proportional to the amount of hydrogen gas evolved [17]. Gasometric experiments were carried out respectively by varying the corrodent (5, 10, 30.50 and 100 mM) and inhibitor concentrations respectively. It can be observed that the higher the corrodent concentration the higher the volume of gas evolved per minute at room temperature. The results of the effect of temperature variation in the absence of Di octylsulphide in 0.5 N HCl solution. It is evident that higher temperature of provided higher volume of hydrogen gas per minutes resulting into a higher rate of reaction. Di octylsulphide systems were tested. To establish, regardless of temperature or corrodent concentration, the higher the volume of gas evolved per minutes the higher the rate of reaction. Concentration increases also inhibitor efficiency increases and corrosion rate decreases [18].

From the gasometry experiments, the inhibition efficiency is calculated by using the following equation.

$$\text{I.E (\%)} = [V_0 - V_i / V_0] 100$$

Where V_0 and V_i are the volume of hydrogen gas evolved in the absence and presence of the inhibitor respectively.

2.5 Thermometric measurement

The reaction vessel is a three-necked round bottom flask and the flask was well lagged to prevent heat losses. In this technique the corrodent (HCl) concentration was also at 0.5N and different concentration 5, 10, 30, 50 100 mM of inhibitors respectively [19]. The volume of the test solution used was 100 cm^3 . The initial temperature in all the experiments was kept at room temperature. The progress of the corrosion reaction was monitored by determining the changes in temperature with time (each minute for the first five minutes, each five minutes for the next 25 minutes and each ten minutes for the last thirty minutes) using a calibrated thermometer (0 - 100°C) to the nearest $\pm 0.05^\circ\text{C}$. The data was generated for a period of one hour. This method enabled the computation of the reaction number (RN). From the rise in temperature of the system per minute, the reaction number (RN) was calculated using equation.

$$\text{RN} = T_m - T_i / t$$

Where T_m is the maximum temperature, T_i is the initial temperature and t is the time taken to attain the maximum temperature. The inhibition efficiency is calculated by using the following equation

$$\text{I.E (\%)} = \text{RN}_0 - \text{RN}_i / \text{RN}_0$$

Where RN_0 is the reaction number in the absence of the inhibitor and RN_i is the reaction number in the presence of various concentrations of the inhibitor.

2.6 Surface morphology

The surface micrographs of the zinc specimens in different test solutions were obtained by SEM. SEM provides a pictorial representation of the surface of the zinc metal to understand the nature of the surface film in the absence and presence Di octylsulphide inhibitor. The scanning electron microscopy

photographs were recorded at 10,000 x magnification using SEM ULTRA-60 nanofab, and Hitachi scanning electron microscopes. AFM measurement was performed using a Bruker Icon Dimension with the Scan Asyst module including tapping mode. The scan rate and area of the images were 0.6 Hz and 5 μm × 5 μm, respectively [20].

3. RESULTS AND DISCUSSION

3.1 Weight loss, gasometry and thermometric studies

Weight loss, gasometry and thermometric studies were conducted and the inhibition efficiency (IE) values were calculated. Values of inhibition efficiency obtained from these experiments are presented in the table-1

Table 1 Values of inhibition efficiency (I.E (%)) obtained from various weight loss, gasometric, thermometric experiments.

Method Employed	Values of I.E(%)different Concentrations (mM) of Di octylsulphide inhibitor				
	5	10	30	50	100
Weight loss	37.0	58.5	73.9	81.7	93.2
Gasometry	36.4	47.2	63.0	70.2	81.1
Thermometry	37.4	48.8	62.4	69.8	81.9

It can be observed from the table 1 that there is very good agreement between the values of inhibition efficiency obtained from these three methods. The results show that the inhibition efficiency increases with increase in the inhibitor concentration. The dependence of inhibition efficiency of the inhibitor concentration is shown in figure-1




Figure 1 Variation of inhibition efficiency with concentration of the di octylsulphide inhibitor for zinc in 0.5 N HCl.

Values of corrosion rates obtained from the weight loss experiments for the inhibitor for the corrosion of zinc in 0.5N HCl in the presence of different concentrations of the inhibitor are presented in the table-2

Table 2 Values of corrosion rates obtained from the weight loss experiments.

Values of corrosion rates and different concentrations (mM) of di octylsulphide inhibitor				
5	10	30	50	100
92.0	79.6	54.3	42.8	30.5

From the table-2 it can be seen that the corrosion rates for the corrosion of zinc in 0.5N HCl decreases with increasing concentration of the inhibitor. The effect of inhibitor concentration on the corrosion rates is shown in figure-2.




Figure 2 Variation of corrosion rates with concentration of the di octylsulphide inhibitor for zinc in 0.5 N HCl.

The inhibitor molecule contains four nitrogen atoms in its molecular structure. These nitrogen atoms possess lone pairs of electrons required for the adsorption process. On adsorption strongly adherent layer is formed on the metal surface. This layer acts as a barrier between the metal and the environment giving protection to the metal. In addition to these, the amino groups present in the molecule can be easily protonated in acid medium to form the cationic form of the inhibitor. The chloride ions present in the acid medium gets adsorbed specifically on the positively charged metal surface due to its lesser degree of hydration leading to the creation of excess negative charges on the metal surface which enhances more adsorption and hence protection of the metal. Another factor responsible for the higher inhibition efficiency of the inhibitor is the large surface area of the inhibitor molecules which provides higher surface coverage to the metal after getting adsorbed on to the metal surface. The structure of the inhibitor is shown in figure 3




Figure 3 The structure of the di octylsulphide inhibitor

3.2 Analysis of SEM

SEM provides a pictorial representation of the zinc metal surface. The SEM images of zinc specimens immersed in 0.5 N HCl for 30 min. in the absence and presence of di octylsulphide inhibitor systems is shown in Figures 4c, respectively. The SEM micrograph of the polished zinc surface in Figure.4a show the smooth surface of the metal, without any corrosion inhibitor, smooth surface of zinc metal and decrease the corroded area of zinc metal. The SEM micrographs of the zinc surface immersed in 0.5 N HCl (Figure 4b) show the roughness of the metal surface, with highly corroded areas. However, Figure 4c shows that in the presence of 5 mM Di octylSulphide, the inhibition efficiency is enhanced, as seen from the decrease in the corroded areas.




Fig. 4: Scanning electron micrographs of zinc immersed for 30 minutes (a) polished Zinc (b) zinc metal immersed in 0.5 N HCl (c) zinc metal immersed in 0.5 N HCl with 5 mM Dioctyl Sulphide inhibitor

In the presence of the 5 mM Dioctyl sulphide inhibitor, the surface is covered by a thin layer of inhibitor that effectively controls the dissolution of the zinc [21,22].

3.3 Atomic force microscopy analysis

AFM is a powerful technique to investigate the surface morphology at the nano-to micro-scale and has become a new choice to study the influence of the inhibitor on the generation and the progress of the corrosion at the metal solution interface. Three dimensional (3D) AFM morphologies for a polished zinc surface (reference sample), a zinc surface immersed in 0.5 N HCl (blank) and zinc surfaces immersed in 0.5 N HCl containing 5 mM dioctyl sulphide inhibitor is shown in Figure 5a, b, and c, respectively. The roughness of the zinc coupons for the polished plate, in the presence of HCl, and with added 5 mM dioctyl sulphide inhibitor is 15.9 nm, 181 nm, 33.4 nm and 28 nm, respectively. This finding indicates that the addition of the different concentration inhibitor reduces the surface roughness, with the di octylsulphide inhibitor providing better protection [23-25].



Fig. 5: AFM 3D images of zinc immersed for 30 minutes (5a) polished coupon, (5b) zinc metal immersed in 0.5 N HCl, (5c) zinc metal immersed in 0.5 N HCl with the addition of 5 mM Dioctyl sulphide inhibitor.

3.3 .ADSORPTION ISOTHERMS

From the weight loss measurements, the degree of surface coverage (θ) for various concentrations of the inhibitor were determined. Temkin's adsorption isotherm was tested by plotting $\log C$ vs θ which gave a straight line thereby indicating that the adsorption of the inhibitor on the surface of zinc from 0.5N HCl obeys Temkin's adsorption isotherm. Figure -6 shows the Temkin adsorption isotherm plot for zinc in 0.5N HCl containing different concentrations of the inhibitor.




Figure 6. Temkin adsorption isotherm plot for zinc in 0.5N HCl containing different concentrations of the inhibitor.

4. CONCLUSION

Di octylsulphide used as a corrosion inhibitor in controlling the control of zinc metal in 0.5 N HCl. The inhibition efficiency and corrosion rates determined by weight loss, gasometric, and thermometric methods. All these techniques indicates that 0.5 N concentration of inhibitor exhibit 93.2 % inhibitor efficiency and 30.5 % corrosion rates. The concentration of the inhibitor increases, the inhibitor efficiency increases and corrosion rate decreases. Performed well and gave high percentage of inhibition efficiency. The indicates that protective film formed over the zinc metal surface. The protective film was characterized by SEM and AFM. The adsorption of the inhibitor on to zinc surface obeyed Temkin adsorption isotherm.

REFERENCES

1. A. S. Fouda, S. Rashwan , A. Emam , F. E. E-Morsy, Corrosion Inhibition of Zinc in Acid Medium using some Novel Organic Compounds, *Int. J. Electrochemist. Sci.*, 13, 3719 – 3744, 2018
2. C X Sun, J J Du , Z W Ma , C S Huang and J Y Wu, Cetyltrimethyl Ammonium Bromide as Corrosion Inhibitor for Zinc Used in Hydrochloric Acid, *International Conference on Computer Information and Automation Engineering, Materials Science and Engineering*, 359, 2018
3. Hadeel Adil, Corrosion Inhibition of Zinc Metal in 2M Hydrochloric Acid Solution by Using Guaifenesin Drug as an Inhibitor and Theoretical Calculations, *Journal of Al-Nahrain University* 18 (1), 60-65, 2015
4. H. Adil, Corrosion inhibition of zinc metal in 2M hydrochloric acid solution by using Guaifenesin drug as an inhibitor and theoretical calculations, *Journal of AlNahrain University*, 18, 60-65, 2015
5. Khulood AL-Saadie, Nadia Abdul Karime and Israa M Al-Mousawi. Corrosion inhibition of zinc in hydrochloric acid medium using urea inhibitor, *Journal of Al-Nahrain University*, 10(2), 31-38, 2007
6. E. Stupnisek-Lisac, S. Podbrscek, T. Soric, Non-toxic organic zinc corrosion inhibitors in hydrochloric acid, *Journal of Applied Electrochemistry*, 29(8), 779–784, 1994
7. C.X. Sun, J.J. Du, Z. W ma, C S Huang and J Y Wu, Cetyltrimethyl ammonium bromide as corrosion inhibitor for zinc used in hydrochloric acid, *international conference on computer information and automation engineering*, 359, 1757-899, 2018
8. Khulood A.Saleh, Khalils. Khalil, Corrosion inhibition of zinc in hydrochloric acid solution using ampicillin, *journal of science*, 55(2a), 295-303, 2014
9. M. Abdallaha, b, I. A. Zaafaranya, , B.A. AL Jahdalya, Corrosion Inhibition of Zinc in Hydrochloric Acid using some, *Antibiotic Drugs, J. Mater. Environ. Sci.* 7 (4) , 1107-1118 , 2016
10. A. S. Fouda¹, S. M. Rash wan, M. M. Kamel and N. M. Arman, Adsorption and Inhibition Behavior of Avicennia Marina for Zn Metal in Hydrochloric Acid Solution, *Int. J. Electrochemist. Sci.*, 12, 11789 – 11804, 2017
11. Jamiu Odusote, Olaoluwa S Ayand, Yahiya Raheem Abolore, Inhibition of Corrosion of Galvanized Steel Sheet in 1M HCl and H₂SO₄ by Plukenetia conophora Leaf Extract, *African corrosion journal*, 2016
12. A. O. James and N. C. Oforka, 2-Benzoyl pyridine: An inhibitor for mild steel corrosion in hydrochloric acid solution, *Advances in Applied Science Research*, 5(2), 1-6, 2014
13. A.p.i popoola and o.s.i fayomi, electrochemical study of zinc plate in acid medium: inhibitory effect of bitter leaf (*vernonia amygdalina*), *int. j. electrochemist. sci.*, 6, 4581 – 4592, 2011
14. Y.K. Agrawal, J.D. Talati, M.D. Shah, M.N. Desai & N.K. Shah, Schiff base of ethylene diamine as corrosion inhibitors of Zinc in sulphuric acid, *Corrosion Science*, 46, 633-651, 2003.
15. Anurag Sharma¹ , Anil Kumar Varshney , Sarita Varshney, Inhibition of Zinc by Natural Oil in 0.5N Hydrochloric Acid and 0.5N Sulfuric Acid, *Int. J. Pharm. Sci.*, 44(2), 148-152, 2017
16. R. A. Prabhu, T. V. Venkatesha, and B.M. Praveen, Electrochemical Study of the Corrosion Behavior of Zinc Surface Treated with a New Organic Chelating Inhibitor, *International Scholarly Research Network*, 2012
17. Inhibition of Zinc Corrosion in Hydrochloric Acid by Some Ligands and Complexes, A.S.M.Diab, H.M.Osman, Abdou Saad El-Tabl, *Original Research Paper Chemistry*, 5(8), 2016
18. N.O. Eddy & S.A. Odoemela, Norfloxacin and Sparfloxacin as corrosion inhibitors for zinc, Effect of concentrations and temperature, *Journal of Materials Science*, 4, 87-96, 2008.
19. R. T. Vashi and krunal desai, hexamine as corrosion inhibitor for zinc in hydrochloric acid, *scholars research library der pharma chemical*, 4(5), 2117-2123, 2012
20. Prathibha B.S, P.Kotteeswaran, V. Bheema Raju, Study on the inhibition of Mild Steel Corrosion by Cationic Surfactant in HCl Medium, *IOSR Journal of Applied Chemistry* 2(1), 45-53, 2012
21. D. Filotás, B.M. Fernandez Perez, J. Izquierdo, A. Kiss, L. Nagy, G. Nagy and R.M. Souto Improved potentiometric SECM imaging of galvanic corrosion reactions *Corrosion Science*, 2017
22. Michel Prestat, Josiane Soares Costa, Benoit Lescop, Stéphane Rioual, Lorenz Holzer and Dominique Thierry Cathodic Corrosion of Zinc under Potentiostatic Conditions in NaCl Solutions, *ChemElectroChem* 10, 2018
23. S. Velu, K. Rambabu, L. Muruganandam, Development, Characterization and Application Studies of Cellulose acetate – activated Carbon blend Ultra Filtration Membranes, 6, 565-577, 2014
24. Qhatan A. Yousif and Adel A. Al-Zhara, Electrochemical Methods, Sem-Eds And Afm Studies For Assessing Corrosion Inhibition Of Carbon Steel In Acidic Media, *ARPN Journal of Engineering and Applied Sciences*, 11, 2016
25. S.V. Lamaka, M.L. Zheludkevich, K.A. Yasakau, High effective organic corrosion inhibitors for 2024 aluminium alloy, *Electrochemical* 52, 7231–7247, 2007