

# FORMULATION AND EVALUATION OF CURCUMIN LOADED SOLID LIPID NANOPARTICLES BY EMPLOYING CUTINA® HR AND TWEEN 80

Shruti Madderla<sup>1</sup> & Dr. P. Tripura Sundari<sup>2</sup>

<sup>1</sup>M.Pharmacy, <sup>2</sup>Associate Professor

Department of Pharmaceutics, R.B.V.R.R Women's College of Pharmacy, Barkatpura, Hyderabad , Telangana, India.

Received: August 23, 2018

Accepted: October 10, 2018

## ABSTRACT

*The aim of the present study is to formulate and evaluate solid lipid nanoparticles of Curcumin. Curcumin has many potential pharmacological effects including anti-inflammatory, antibacterial, antioxidant and anticancer activities. Curcumin has poor water solubility and oral bioavailability. Therefore, the delivery of drug molecules through the carrier systems avoid unwanted effects because of controlled biodistribution. Development of efficient drug delivery system for curcumin would be a potential approach to improve its bioavailability and clinical efficacy. To overcome these problems an attempt was made to prepare Curcumin into Solid lipid nanoparticles which has ability to improve the solubility and enhance the oral bioavailability.*

*In the present study Curcumin loaded SLNs was prepared by Hot Homogenization method. The Cutina® HR was used as the Lipid, Soya lecithin as lipophilic surfactant, and Tween 80 as Hydrophilic surfactant in the preparation. The four prepared formulations were evaluated for various parameters like Drug content, entrapment efficiency, In Vitro drug release and the best formulation was further analysed by instrumental methods such as particle size determination, zeta potential and also for SEM analysis. Among all the Preparations, T3 formulation was best in terms of Entrapment efficiency with 85.2%, Drug release of 75.7%, in-vitro drug release of 82.6% for 24hrs, particle size of 155.9nm of and with a stability of -30.9mV. The present study conclusively demonstrated that the solubility of drug was improved by entrapment of drug into solid lipid carrier which led to prolongation of drug release.*

**Keywords:** Solid Lipid Nanoparticles, Curcumin, Cutina® HR.

## INTRODUCTION

Oral administration of the drug is most convenient way and commonly used route for the delivery of the drugs because its advantages like ease of administration, high patient compliance, cost effectiveness etc.[1] The major challenge in designing the oral dosage form lies with their poor bioavailability. The oral bioavailability depends on several factors like aqueous solubility, dissolution rate, first pass metabolism, drug permeability, pre systemic metabolism etc. But most often cause of the low oral bioavailability is due to poor solubility and low permeability. Thus to overcome this problem of oral bioavailability the solubility of drug must be enhanced.

There are several techniques to enhance solubility there by bioavailability of the poorly soluble drugs. Novel techniques possess advantages over traditional techniques. Various novel techniques that are used to enhance the solubility are like solid lipid nanoparticles, Self emulsifying drug delivery systems, solid dispersions etc. Depending upon the problem associated with the drug the technique that is to be employed must be chosen. Here we chose solid lipid nanoparticles for the study of this drug Curcumin.

Curcumin is a natural compound obtained from *Curcuma longa* Linn which has wide therapeutic activities and practically insoluble in water and has poor bioavailability; it is a biopharmaceutics classification system (BCS) class-IV drug [2,3]. This class of drugs shows dissolution rate limited absorption and hence variable bioavailability [4,5]. To overcome these drawbacks, increasing the dissolution rate and aqueous solubility of curcumin is an important goal [6,7]. Possible methods to avoid first pass metabolism include transdermal, buccal, rectal and parenteral route of administration. But the oral route is considered as the natural, convenient and safest route of administration involving higher patient compliance with lesser complications.[8] The conventional preparations like solution, suspension or emulsion for drug delivery purpose has various boundaries like high dose and low availability, faster reach effect etc. The changes in blood plasma drug levels are also exhibited which do not provide sustained effect as well as reaching of drug to target site without any alteration in its physical and chemical properties.

Therefore, there is a need for some novel carriers which could improve the above problems by reaching to its target site without making any adverse effects to body and can carry the drug easily and safely to its destination. Nanoparticles (NP) are a type of colloidal drug delivery system comprising particles with a size range from 10 to 1000 nm (diameter). The major advantages of nanoparticles are improved bioavailability

by enhancing aqueous solubility, increasing resistance time in the body (increasing half life for clearance/increasing specificity for its associated receptors and targeting drug to specific location in the body). This is why nanoparticles are increasingly used in variety of applications that includes drug carrier systems and to pass organ barriers such as the blood-brain barrier, cell membrane etc. They are based on biocompatible lipid that provide sustained effect by either diffusion or dissolution.[4,5] Moreover it can be said that nanoparticles are now a day's acting as very prolific device for drug delivery system.

Solid Lipid nanoparticles have ability to overcome the challenges associated with oral delivery of drugs that have low solubility, poor permeability, instability in the GIT and pre-systemic drug metabolism.[6] Thus to overcome the problems that are associated with drug Curcumin like low solubility and poor oral bioavailability, the Curcumin loaded solid lipid nanoparticles were prepared which are capable of improving above mentioned properties.

In the current study, the Curcumin loaded SLNs were prepared using cutina® HR as lipid and surfactants like Soya lecithin, Tween 80 and carbopol by hot homogenization followed by sonication. The prepared SLN were characterized and evaluated for various parameters like Drug content, entrapment efficiency and invitro drug release.

## MATERIALS AND METHODS

### 2.1 Materials

Curcumin was purchased from HiMedia laboratories, Cutina® HR (BASF), Soya lecithin (HiMedia laboratories), Tween 80 (S.D. fine chemicals) and dialysis membrane (HiMedia, Mumbai). All other reagents used were of analytical grade.

### 2.2 Preparation of Curcumin loaded solid lipid nanoparticles

Curcumin loaded SLNs were prepared by Hot homogenization method followed by sonication.

#### Hot Homogenization Method

Hot homogenization method is best suited method for the preparation of solid lipid nanoparticles as it can be performed at elevated temperatures to that of lipids melting point. The reduction in the particle size is due to cavitations and turbulences during homogenization.[9] In hot homogenization technique the drug was dispersed in the lipid (Cutina HR) and Soya lecithin (surfactant) by melting them above 5°C of their melting point. This is considered as oil phase. The aqueous phase was prepared by adding hydrophilic surfactant (Tween 80) in the distilled water and heated to the temperature of oil phase. The prepared oil phase was added to the aqueous phase drop by drop under continuous stirring at 2700 rpm for about 3hrs. The prepared formulation was further sonicated for half an hour and cooled to room temperature. At the room temperature the lipid recrystallizes and leads to formation of SLNs. Formulations prepared by Hot homogenization was coded as T1 to T4. The various formulations are shown in table 1.

Formulation Code	Ratio (lipid : lipophilic surfactant: hydrophilic surfactant)
T1	1:1:1
T2	1:1:2
T3	1:2:1
T4	1:2:2

**Table 1: Composition of Curcumin loaded SLN formulations by hot homogenization.**

In all SLN formulations, curcumin was equivalent to 10mg.

### Evaluation of Solid Lipid Nanoparticles

**Drug content:** 1ml of the formulation was added to methanol and made it to 10ml. The suitable dilutions were made with phosphate buffer saline of pH 7.4 and the concentration of the drug was analyzed using UV-visible spectrophotometer at 430nm.

#### Entrapment Efficiency

Entrapment efficiency is an important parameter for characterizing solid lipid nanoparticles. This parameter gives us an idea of the drug that was entrapped in SLNs by the carrier. In order to attain optimal entrapment efficiency, the varying concentrations of lipid to lipophilic surfactant to hydrophilic surfactant ratio were used. The entrapment efficiency of prepared SLNs was determined by the centrifugation method. SLNs (containing equivalent to 10mg of drug) was centrifuged at 10000rpm for 40min in high speed research centrifuge to collect supernatant liquid. The collected liquid was filtered to measure amount of free drug concentration after suitable dilution with the fresh phosphate buffer saline of pH 7.4. The absorbance

was measured at 430 nm in a UV-visible spectrophotometer to calculate the entrapment efficiency using the formula:

$$E.E = \frac{\text{Amount of total drug} - \text{Amount of drug in aqueous phase}}{\text{Amount of total drug}} \times 100$$

### In vitro Drug Release

The in vitro drug release of Curcumin loaded SLNs was determined by dissolution apparatus using USP II with the help of dialysis bag dissolution technique. An accurate 1ml of Curcumin SLNs was taken into the dialysis bag and sealed. This sealed dialysis bag was then suspended into the dissolution basket containing 900ml of phosphate buffer saline solution of pH 7.4 at the temperature of  $37 \pm 2^\circ\text{C}$ , and stirred at a constant speed of 100rpm. Aliquotes were collected at the time intervals like 0.5,1,2,3,4,5,6,7,8,9,10,11,12 up to 24 hours and the same was replaced with the fresh buffer. The drug content was determined spectrophotometrically by measuring the absorbance at 430nm using the same buffer solution as the blank, to calculate the amount of drug released from the nanoparticles.

### Measurement of particle size:

The mean diameter of solid lipid nanoparticle in the dispersion was determined by MALVERN Nano Particle analyzer. Before the measurement one drop of sample was taken from each formulation and diluted in 10ml of dispersion medium (double distilled water). Dynamic Light Scattering (DLS), also known as Photon Correlation Spectroscopy, is a common technique for measuring the size of particles in sub micron range. It measures Brownian motion of particles, suspended in a liquid through the changes in the intensity of light scattered from particles through time. Consequently, the slower the motion the larger the particle will be, since smaller particles are more affected by interactions with the solvent. Considering this motion, and the temperature and viscosity of the sample throughout the analysis, DLS can calculate the hydrodynamic diameter of the particle.

### Measurement of zeta potential:

The zeta potential is a physical property, exhibited by all particles in the preparation. It was analysed by MALVERN instrument. It is an important factor to be considered in understanding the electric double layer repulsion and it can be measured by phase analysis light scattering. When an electric field is applied across an electrolyte, charged particles in preparation are attracted towards the electrode of opposite charge while viscous forces acting on the particle tend to oppose the movement. When equilibrium is reached, the particles move with constant velocity, also known as electrophoretic mobility, and the zeta potential can be measured. The magnitude of the zeta potential is large, the particles in preparation will tend to repel each other. Hence, there will be no tendency to agglomerate. Contrastingly, when zeta potential values are low, it means that there will be no force acting to prevent the particles coming together and agglomerate.

### MORPHOLOGY OF NANOPARTICLES:

Scanning electron microscopy (SEM) is based on the incidence of a beam of accelerated electrons on the sample. This was analysed by Shimadzu corporation, Japan.

### Kinetic Studies: Mathematical models

Different release kinetic equations (zero-order, first-order, Higuchi's equation and Korsmeyer-peppas equation) were applied to interpret the release rate of the drug from matrix systems for the optimized formulation. The best fit with higher correlation ( $R^2$ ) was calculated.

### Fitting Data Into Kinetic Models


The obtained drug release data was fitted into various kinetic plots (zero order, first order, Higuchi and Peppas) in order to determine the order and mode of drug release from the formulated SLNs.

## RESULTS AND DISCUSSION

**Drug content:** The drug content of all the prepared SLN formulations by hot homogenization is shown in Table 2

FORMULATION CODE	DRUG CONTENT(%)
T1	65.0
T2	72.4
T3	85.2
T4	67.6

**Table 2: Drug content of curcumin loaded SLNs by hot homogenization**



**Fig 1: Comparison of drug content of curcumin loaded solid lipid nanoparticles**


The drug content of all formulations were found to be 65.0%, 72.40%, 85.20% and 67.60%. Among all the formulations, T3 has shown greater drug content. As T3 formulation has the proportion of 1:2:1 for lipid to lipophilic surfactant to hydrophilic surfactant concentration, maximum amount of the drug content was found in this ratio.

**Comparison of entrapment efficiencies of curcumin loaded solid lipid nanoparticles.**

Entrapment efficiency defines the amount of drug that has been entrapped in the polymer matrix.

FORMULATION CODE	% ENTRAPMENT EFFICIENCY (%)
T1	62.9
T2	68.3
T3	75.7
T4	73.0

**Tab 3: Entrapment efficiencies of curcumin loaded solid lipid nanoparticles by Hot Homogenization Method**



**Fig 2: Comparison of Entrapment efficiencies of curcumin loaded solid lipid nanoparticles**


The entrapment efficiencies of all formulations were found to be 62.90%, 68.30%, 75.70% and 73.0%. Among all the formulations, T3 has shown greater entrapment efficiency. As T3 formulation has the proportion of of 1:2:1 for lipid to lipophilic surfactant to hydrophilic surfactant concentration, maximum amount of the drug was entrapped in the lipid. The lipid concentration was found to be sufficient to entrap the drug into it.

**In vitro drug release studies of curcumin loaded solid lipid nanoparticles.**

In vitro drug release studies were carried by dissolution apparatus using USP II (Paddle). Samples were collected at time intervals like 30min, 1, 2,4,6,8,10,12,24 hours. Medium used for dissolution was pH 7.4 phosphate buffered saline, temperature 37±2°C, rpm of 100 at wave length of 430nm.

Time interval (hr)	T1	T2	T3	T4	P.D
0	0	0	0	0	0
0.5	7.2±0.03	8.7±0.04	9.2±0.04	7.9±0.02	0.1±0.08
1	10.2±0.02	11.9±0.07	12.8±0.01	10.4±0.06	0.5±0.01
2	15.6±0.06	18.1±0.04	19.4±0.06	17.9±0.01	5.3±0.03
4	22.4±0.04	25.8±0.06	26.1±0.05	24.10±0.04	7.5±0.05
6	31.6±0.01	36.5±0.01	38.7±0.02	32.7±0.03	9.6±0.07
8	40.0±0.08	47.2±0.05	49.9±0.03	43.1±0.02	13.0±0.06
10	46.8±0.07	51.3±0.07	57.8±0.04	49.0±0.01	15.1±0.01
12	52.9±0.02	58.8±0.02	60.1±0.02	56.4±0.05	17.8±0.03
24	72.0±0.06	79.2±0.01	82.6±0.07	77.9±0.04	33.7±0.04

**Tab 4: Invitro drug release studies of curcumin loaded solid lipid nanoparticles with pure drug by hot homogenization**



**Fig.3: Comparative drug release of pure drug and prepared formulation (C4).**


**CHARACTERISATION OF OPTIMISED FORMULATION FOR INSTRUMENTAL ANALYSIS**

Among all the prepared formulations, the optimised formulations was found to be T3, formulation as it has shown better results for drug content, entrappment efficiency and percentage drug release than other formulations.

It was further analysed by instrumental methods including particle size determination, zeta potential, Scanning electron microscope. These were further applied to the kinetic models.

**PARTICLE SIZE DETERMINATION OF FORMULATION T3**


Among the five prepared formulations, the particle size of the T3 was considered as the best formulation with the particles of size of 155.9nm. Particle size analysis was determined by MALVERN nanoparticle analyser. Thus it was observed that formulation was found to be in nano range.



**Fig 4: particle size report T3 formulation of curcumin loaded SLN by Hot homogenization method**


### DETERMINATION OF ZETA POTENTIAL OF FORMULATION T3

The zeta potential value indicates the stability of nanoparticles. It was determined by MALVERN nanoparticle analyzer. The formulation T3 has shown a zeta potential value of -30.4mV which shows that the formulation is stable.



**Fig 5 : Zeta potential report T3 formulation of curcumin loaded SLN by Hot homogenization method**

### SCANNING ELECTRON MICROSCOPEY(SEM) ANALYSIS OF FORMULATION T3







**Fig 6: SEM images of formulation T3**

The sample was analysed for SEM to know the surface morphology. SEM results are also in accordance with particle size and was observed in spherical shape.

### FITTING DATA INTO KINETIC PLOTS OF CURCUMIN LOADED NANOPARTICLES OF ALL OPTIMISED FORMULATIONS

The drug release data was fitted in various kinetic plots (Zero order, First order, Higuchi and Korsmeyer Peppas plots) which were drawn for the optimised formulation T3 in order to determine the order and mode of drug release.

**KINETIC PLOTS OF FORMULATION T3**



Formulation	Zero order (R <sup>2</sup> )	First order(R <sup>2</sup> )	Higuchi plot(R <sup>2</sup> )	Peppas plot(n)
T3	0.596	0.928	0.945	1.611

**Table No 5:- Kinetic release data for optimized formulation T3**

According to the kinetic plots, the optimized formulation T3 was following the First order release with non-fickian diffusion mechanism.

**CONCLUSION**

In the present research, the different formulations were prepared by using Cutina HR, by employing hot homogenization method. The entrapment efficiency and drug release profile were depended up on the concentration of lipid and surfactant mixture employed. The results of in-vitro drug release studies demonstrated significantly controlled release of Curcumin from prepared SLNs. Among all the Preparations T3 formulation was best in terms of drug content of 85.2%, Entrapment efficiency of 75.7 % and % Drug release of 82.6% in Hot Homogenization with a particle size of 155.9nm and a zeta potential of -30.9mV.

SEM results were also in accordance with particle size and was observed in spherical shape. The drug release data revealed that a good regression was obtained for first order kinetics and Higuchi equation, which indicated that the formulation released drug in sustained release concentration dependent mode and drug release from lipid matrix was Higuchi diffusion. Release exponent, 'n' value of T3 formulation is greater than 0.5 indicating that release followed non fickian diffusion which Supports the Super case II mechanism (r<sup>2</sup> value was 0.928, n value was found to be 1.611 for T3 in hot homogenization method).

Hot homogenization was found to be the best method as particle size obtained was small, with high entrapment efficiency value which may be because of better association of surfactant with lipid particles. This method was found to be simple, cost effective, easy and suitable to produce SLNs. This method can be scaled up when compared with other preparations. Further it could be presumed that the obtained nanoparticles might increase oral bioavailability. Hence SLNs can be formulated Successfully by employing this Hot homogenization technique.

#### REFERENCES:

1. S. R. K. Yellela, "Pharmaceutical technologies for enhancing oral bioavailability of poorly soluble drugs," *Journal of Bioequivalence & Bioavailability*, 2010; 2(2): 28-36.
2. Ruby A.S, Kutan G, Babu KD, Rajasekharan KN, Kuttan R, Antitumour and antioxidant activity of natural curcuminoids, *Cancer Lett* 1995; 94, 79 – 83.
3. Subramanian L, Sivam R, Prevention of CCl<sub>4</sub> – Induced hepatotoxicity by aqueous extract of turmeric, *Nutra-Res*, 1999; 19, 429 -441.
4. Amidon G. L, Lenernas H, Shah VP, Crison JR, A theoretical basic for a biopharmaceutic drug classification: the correlation of in vitro drug product dissolution in vivo bioavailability, *Pharmaceutical Research*, 1995,12 ; 413 – 420.
5. Arun G, Shweta P, Upendra KJ, Formulation and Evaluation of Ternary Solid Dispersion of Curcumin, *Int. J Pharm Pharma Sci*, 2012, 4, (5) ; 360-365
6. Ajay S, Harita D, Tarigue M, Amin P, Solubility and dissolution rate enhancement of curcumin using kollidon VA64 by solid dispersion technique, *Int. J. Pharm.Tech Res*, 2012, 4 (3), 1055 – 1064.
7. Joshi V, Ahmed GA, Suresh S, Kowti R, A comparative study : solution stability and dissolution behavior of solid dispersion curcumin, *Indian J Nov Drug Deliver*, 2010, 2 (3), 88 – 95.
8. Arjun Narala and Kishan Veerabrahma, Preparation, Characterization and Evaluation of Curcumin Solid Lipid Nanoparticles to Improve the Oral Bioavailability, *Journal Of Pharmaceutics*, <http://dx.doi.org/10.1155/2013/265741>.
9. P. Ekambaram, A. Abdul Hasan Santhali and K. Priyanka. Solid lipid nanoparticle: A review. *Sci. Revs. Chem. Commun.*, 2012; 2(1): 80-102.
10. Zur Muhlen A, Schwarz C, Mehnert W. Solid lipid nanoparticles (SLN) for controlled drug delivery – Drug release and mechanism. *Eur J Pharm Biopharm.*, 1998; 45: 149-55.
11. P Senthil Kumar and N Punniamurthy: Formulation development and characterization of curcumin loaded solid lipid nanoparticles for improved aqueous solubility and bioavailability; *The Pharma Innovation Journal* 2017; 6(4): 07-11
12. PRAGNA shelata, VINOD K. Mandowaraa\*, DEEPAK G. Gupta, SHETULV. Patela ; Formulation of curcuminoid loaded solid lipid nanoparticles in order to improve oral bioavailability; *international journal of pharmacy and pharmaceutical sciences* ;2015 ;vol 7, issue 6
13. Daniela Chirio , Marina Gallarate, Elena Peira , Luigi Battaglia , Loredana Serpe and Michele Trotta; Formulation of curcumin-loaded solid lipid nanoparticles produced by fatty acids coacervation technique; *Journal of Microencapsulation*, 2011; 28(6): 537-548s Curcumin-loaded solid lipid nanoparticles with Brij78 and TPGS improved in vivo oral bioavailability and in situ intestinal absorption of curcumin; *Informa Healthcare* 2014;23(2): 459-470
14. Sarabjot kaur, Ujjwal Nautyal\*, Ramandeep Singh, Satvinder Singh, Anita Devi; Nanostructure Lipid Carrier (NLC): the new generation of lipid nanoparticles; *Asian Pac. J. Health Sci.*, 2015; 2(2): 76-93